

**SWEATTABSORBING POLYESTER FIBER**

**Patent number:** JP55107510  
**Publication date:** 1980-08-18  
**Inventor:** SHIZUKI TATSUHIKO; NANRI SHIYOUSUKE; OONO TERUO  
**Applicant:** TOYO BOSEKI  
**Classification:**  
- international: **D01F6/62; D01F6/62; (IPC1-7): D01F6/62**  
- european:  
**Application number:** JP19790012524 19790205  
**Priority number(s):** JP19790012524 19790205

**Report a data error here**

**Abstract of JP55107510**

**PURPOSE:** To obtain fibers having improved water absorption itself and pilling resistance after alkali treatment, with a specific cross-sectional shape, by incorporating an independent phase of a polyoxyalkylene glycol (derivative) into a specific modified polyester. **CONSTITUTION:** A polyoxyalkylene glycol (derivative) as a substantially independent phase is incorporated into a modified polyester fibers consisting of ethylene terephthalate repeating units mainly, and 0.5-8wt% of a polyoxyalkylene glycol (derivative) to give hollow or modified cross section fibers. The hollow fibers have a degree of hollowness of 5-60%, and modified cross-section fibers have a modification ratio  $[S = \frac{\text{the length (cm) of the contours of the fiber cross-sections}}{\text{the cross-sectional area (cm}^2\text{) of fibers}}] \geq 5000/d^{1/2}$  (d is the denier per fiber). The water and sweat absorption, and light-resistance can be further improved by treatment with an alkali.

Data supplied from the **esp@cenet** database - Worldwide

**DELPHION****RESEARCH****PRODUCTS****INSIDE DELPHION**
[Log Out](#) | [Work Files](#) | [Saved Searches](#)
[My Account](#)Search: [Quick/Number](#) [Boolean](#) [Advanced](#) [Der](#)**The Delphion Integrated View**Get Now: ☒ [PDF](#) | [File History](#) | [Other choices](#)Tools: Add to Work File: [Create new Work](#)View: [INPADOC](#) | Jump to: [Top](#) ☒ Go to: [Derwent](#)[Ema](#)Title: **JP55107510A2: SWEAT-ABSORBING POLYESTER FIBER**Derwent Title: Sweat-absorbing polyester fibre - contains polyoxyalkylene glycol (deriv.) for improved spinning processability ([Derwent Record](#))Country: **JP Japan**Kind: **A**Inventor: **SHIZUKI TATSUHIKO;  
NANRI SHOSUKE;  
ONO TERUO;**Assignee: **TOYOBO CO LTD**  
[News, Profiles, Stocks and More about this company](#)Published / Filed: **1980-08-18 / 1979-02-05**Application Number: **JP1979000012524**IPC Code: **IPC-7: D01F 6/62;**Priority Number: **1979-02-05 JP1979000012524**Abstract: **PURPOSE:** To obtain fibers having improved water absorption itself and pilling resistance after alkali treatment, with a specific cross-sectional shape, by incorporating an independent phase of a polyoxyalkylene glycol (derivative) into a specific modified polyester.

**CONSTITUTION:** A polyoxyalkylene glycol (derivative) as a substantially independent phase is incorporated into a modified polyester fibers consisting of ethylene terephthalate repeating units mainly, and 0.5W8wt% of a polyoxyalkylene glycol (derivative) to give hollow or modified cross section fibers. The hollow fibers have a degree of hollowness of 5W60%, and modified cross-section fibers have a modification ratio [ $S = \frac{\text{the length(cm) of the contours of the fiber cross-sections}}{\text{the cross-sectional area(cm}^2\text{) of fibers}} \geq 5000/d^{1/2}$  ( $d$  is the denier per fiber)]. The water and sweat absorption, and light-resistance can be further improved by treatment with an alkali.

COPYRIGHT: (C)1980,JPO&amp;Japio

Family: **None**Other Abstract Info: **CHEMABS 094(02)004889K**[Nominate this for the Gallery...](#)